

Ice Bath Conversion Kit

Epoxy Conversion Lining for Ice Baths



TECHNICAL DATA SHEET

1. PRODUCT DESCRIPTION & INTENDED USE

An epoxy conversion lining kit using the industrial-grade, fish- and plant-safe Pond Epoxy to convert a vessel into a durable, waterproof, easy-clean ice bath. Cures underwater and resists continuous immersion.

Note: Exact kit size follows the current website product (brushes and rollers excluded) - to confirm against the live page.

2. KIT CONTENTS & COVERAGE

Kit size per the current website product (consumables excluded). Consider an extra base-coat kit for substandard or damaged concrete surfaces.

Product Description	Size	Code	Qty
Pond Epoxy / Ice Bath Liner	2-4 Lt	CP	1

3. KEY FEATURES & BENEFITS

- Durable, waterproof coating for pools and water features
- Smooth, hygienic and easy-to-clean finish
- UV-stable, colourfast top coat
- Resistant to pool chemicals

4. RECOMMENDED SUBSTRATES & APPLICATIONS

Substrates: Concrete and prepared cementitious floors.

Applications: Ice bath conversions, cold plunge vessels and tanks.

Applied by: Roller, brush or squeegee (minimum two coats).

5. COLOUR CHART

Pond Epoxy standard colours (also available clear):

Colour	Code	Colour	Code
White	N14	Cream	Y34
Bright Blue	B23	Terracotta	R52
Pale Blue	B35	Strawberry	R24
Bluebell	B41	Rose Pink	R25
Sky Blue	B45	Dark Brown	X65
Opaline	G32	Black	N61
Neutral Grey	N23	Dark Grey	N64

Also available in all Australian Standard AS 2700 colours (206). Contact the office for custom tints.

6. TECHNICAL PROPERTIES

Property	Value
Solids content	100% solid (solvent-less)

Ice Bath Conversion Kit

Epoxy Conversion Lining for Ice Baths



Property	Value
Specific gravity of blend	1.4
Compressive strength	900 PSI
Coverage (roller, 300 micron)	~0.3 L of blend per m ²
Maximum surface temperature exposure	140 °C
Lower temperature limit	Stable at sub-zero temperatures
VOC	Resins contain NIL, EpoDil contains 75% VOC

Dry Time at 25 °C

Stage	Time	Notes
Pot life	30 minutes	at 25 °C
Tack free	6-8 hours	
Dry cured	12-24 hours	temperature dependent
Fill with water	48 hours	after final coat
Fully cured	7 days	cures underwater

Note: Designed for underwater use and out of direct sunlight. Where pool chemicals are used, shield with Polyurethane or Chemical Resistant Clear Epoxy. Fish- and plant-safe.

7. SURFACE PREPARATION

Apply only to a clean, dry surface free of dirt, grease, oil, paint, curing agents and other contaminants.

- Grind the concrete to maximise adhesion, or acid-wash to open porosity then wash, rinse and flush to neutralise.
- Run a dry test: tape a plastic sheet over a small area for 1 hour; if no moisture appears, the slab is sufficiently dry.
- Remove all loose material, then vacuum and/or blow out all dust.

Note: New concrete must cure fully (minimum 28 days) before application.

8. MIXING

- Combine the components in accordance with the product label and mix for a minimum of 3 minutes with a slow-speed drill mixer.
- Scrape the sides and base of the container so no unmixed material remains; mix until uniform and free of streaks.
- EpoDil may be added to thin the first coat if required (e.g. on cold days).
- Mix only the quantity that can be applied within the pot life.

9. CLEANING OF TOOLS

- Clean tools and uncured spills with thinner & diluent (blend of solvents).
- In service the seamless surface is easy to maintain - easy mop and easy wipe.

10. HEALTH, SAFETY & HANDLING

- Storage: store out of direct sunlight and heat at all times.
- Shelf life: 24 months (epoxy components). Keep pails sealed when not in use.
- A Material Safety Data Sheet (SDS) is available from Shimicoat on request.

Ice Bath Conversion Kit

Epoxy Conversion Lining for Ice Baths



TO CONFIRM - PPE specification, hazard classification and exact shelf life of all components are not itemised here - refer to the SDS.

11. LIMITATIONS & IMPORTANT NOTES

- Epoxy coatings may yellow in direct sun; use a UV-resistant top coat outdoors to prevent chalking and colour change.
- Do not apply over a patchy (possibly damp) slab - always run the dry test first.
- Do not apply if rain is expected within 24 hours; avoid hot surfaces and direct sun.
- Keep foot traffic off for at least 16 hours and vehicles off for 7 days; avoid dragging furniture for ~2 weeks.

12. CONTACT DETAILS & DISCLAIMER

SHIMICOAT Pty Ltd

Ph (08) 9434 3302 info@shimi.com.au www.shimi.com.au
ABN 28 622 871 283

Disclaimer: The technical data herein is based on tests carried out in our laboratories and is true and accurate to the best of our knowledge on the date of publication, but is subject to change without notice. As the uses of this product are beyond the seller's control, the product is sold without guarantees; warranties are governed by Shimicoat's Standard Terms of Sale. The purchaser must conduct its own tests to determine suitability for their specific application. Shimicoat Pty Ltd accepts no liability beyond replacement of defective product.

Source: Shimicoat product data and shimi.com.au (current product pages take precedence). Kit composition per the 2026 single-kit schedule.