

Fiberglass Clear Epoxy

Shimicoat Product - Technical Data Sheet



TECHNICAL DATA SHEET

1. PRODUCT DESCRIPTION

Shimicoat Fiberglass Clear Epoxy is a clear laminating epoxy for fibreglass work. It is a 100% solid epoxy resin with excellent mechanical, chemical and adhesion properties to most substrates, developed for Australian conditions. It is solvent-free as a clear coating or binder and can be tinted and incorporated with decorative or non-slip materials.

Product code: FG

2. TYPICAL USES

Suitable for: a clear laminating epoxy for fibreglass work.

3. KEY FEATURES & BENEFITS

- Crystal-clear, 100% solid and solvent-free
- Excellent adhesion, hardness and chemical resistance
- Use as a seal / build coat or decorative binder
- Can be tinted and used with flake, quartz, glitter or metallic

4. TECHNICAL PROPERTIES

Property	Value
Solids content	100% solid (solvent-less)
Specific gravity	approx. 1.4
Pot life @ 25 °C	45 minutes
Re-coat	Overnight (16 hours)
Full cure	7 days
Maximum surface temperature	140 °C
UV stability	May yellow in direct sun - topcoat for UV
VOC	not published by manufacturer

Note: Cure times vary with temperature, humidity and film thickness. Mixing ratio is shown on the product label.

5. SURFACE PREPARATION

Apply only to a clean, dry, sound surface free of dust, grease, oil and contaminants. Grind or etch concrete to a key and run a dry test before coating.

6. MIXING & APPLICATION

- Mix the components per the product label for a minimum of 3 minutes with a slow-speed mixer.
- Apply by roller, brush or squeegee within the pot life; maintain a wet edge.
- EpoDil may be added to thin the product where the label permits.

7. CLEANING

- Clean tools and uncured spills with thinner & diluent (EpoDil).

8. HEALTH, SAFETY & HANDLING

Fiberglass Clear Epoxy

Shimicoat Product - Technical Data Sheet



- Store out of direct sunlight and heat. Keep containers sealed.
- A Material Safety Data Sheet (SDS) is available from Shimicoat on request.

TO CONFIRM - PPE, hazard classification and shelf life are not itemised here - refer to the SDS.

9. CONTACT DETAILS & DISCLAIMER

SHIMICOAT Pty Ltd

9a Morse Road, Bibra Lake WA 6163

Ph (08) 9434 3302 info@shimi.com.au www.shimi.com.au

ABN 28 622 871 283

Disclaimer: Information herein is guidance only, based on present knowledge and experience. As use is beyond the seller's control, the product is sold without guarantees; the purchaser must conduct its own tests for suitability. Shimicoat Pty Ltd accepts no liability beyond replacement of defective product.

Source: shimi.com.au product pages (current site takes precedence).