

RESIDENTIAL  
& COMMERCIAL

INDUSTRIAL  
& MARINE

ART  
& CRAFT

**SHIMICOAT**  
SURFACE SOLUTIONS



## Laminating Clear Epoxy

### *An Application Guide*

#### Mixing:

Mix Ratio: 2A:1B by weight or volume. Mix thoroughly for a minimum 3 minutes manual or with mechanical mixer at low speed (750rpm Max). If mixing smaller portions mix at a ratio of 2A:1B by weight. For example, to prepare 1.5Kg mix, add 500g or Part B into 1.0Kg (1,000gr) of Part A. If colour required, add SHIMI COLOURS to the kit and mix again thoroughly.

- Ensure surface to be coated is dry, moisture can cause blooming and delamination.
- Pot life is approximately 45 minutes, work within 30min to ensure easy flow application.
- SHIMI COLOURS, SHIMI METALLIC or SHIMI GLITTERS should be first added to Part A (Resin). Mix slowly using drill mixer on low speed. Mix for a few minutes to ensure completely homogenized without lump. Pour the bend into your tray and apply directly on the surface using the roller.
- Use steady long strokes and avoid overworking the roller or pushing your roller too quickly as this may trap air bubbles in the coating.
- Do not apply if the rain is expected within 24 hours of application.
- Not recommended for use below 10°C or above 35°C.
- New concrete should be allowed to cure fully (at least 20days) before application.
- Keep the pail sealed when not in use. Avoid application on hot surfaces.

#### Curing Times

Laminating Clear Epoxy cures in 8-10 hours. High temperatures and windy conditions may speed the curing time. Keep foot traffic and heavy objects off the final coat for at least 16 hours and vehicles for at least 7 days. Full hardness is achieved within 7 days.

Temp °C	Pot Life (min)	Surface Dry (Hours)	Initial Cure (Hours)	Recoat Time (Hours)	Fully Cured (Days)
10°C	45	12	24	24	7 Days
20°C	40	10	18	18	7 Days
30°C	35	8	16	16	7 Days



MATERIALS



CHEMICALS



RESINS



EQUIPMENT

#### WARNING

- Heavy vehicles with hot tires may cause damage on driveway. Avoid driving over the new coated floors till completely cured (7 Days). For parking the car, place a mat under each tire during the first few weeks to ensure longevity of your new floor.
- Do not apply Laminating Clear Epoxy, if the concrete has a patchy appearance as moisture may be present. Dry Test prior to application.
- Direct sunlight and UV radiation may result in chalking, colour variations and yellowing effect over time. UV resistance topcoat "UVthane PLUS" or Acrylic Sealers shall be used for under sun surfaces.

#### Storage

The products shall be stored out of direct sunlight and heat at all times. The shelf life of the product is 24 months, mix uniformly for 3 minutes prior to use.

#### DISCLAIMER

Material Safety Data Sheet, Technical and Environmental Data Sheet can be provided upon request.

The information provided in this document is guidance only and considering the uses of this product are beyond the seller's control, the product is sold without guarantees or warranties. Warranties and guarantees shall be governed by SHIMICOAT Standard Terms of Sale. The purchaser shall make its own tests to determine the suitability for their specific application, and Shimicoat Pty Ltd is taking no responsibility for misuse of the product. The purchaser assumes all risk of use and handling of this product. This product will be happily replaced or credited back if defective. Beyond this, Shimicoat Pty Ltd is not liable for any damages caused by this product or its use. *This information and all further technical advice are based on our present knowledge and experience.*

*The customer is not released from the obligation to conduct careful inspection and testing of supplied goods.*