

RESIDENTIAL
& COMMERCIAL

INDUSTRIAL
& MARINE

ART
& CRAFT

SHIMICOAT
SURFACE SOLUTIONS



Chemical Resistant Clear Epoxy

Kit Sizes

Kit Size (Vol)	Mix Ratio
750mL	2A:1B (0.5Lt A + 0.25Lt B)
1.5L	2A:1B (1Lt A + 0.5Lt B)
3L	2A:1B (2Lt A + 1Lt B)
6L	2A:1B (4Lt A + 2Lt B)
15L	2A:1B (10Lt A + 5Lt B)
30L	2A:1B (20Lt A + 10Lt B)

Description

Chemical Resistant Clear Epoxy CR130 is an industrial grade epoxy coating material for high performance floors. The product has various applications due to its excellent mechanical, chemical, electrical and adhesion properties to most substrates.

Two components (A & B) comes in clear 100% solid epoxy used as clear topcoat with chemical resistance and durability, ideal for variety of floor coating systems. Chemical Resistant Clear Epoxy CR130 is a high-quality solvent-less, odorless two component coating system for concrete surfaces such as driveways, pathways, workshops and warehouses providing a tough clear film, high gloss and wet look to protect surface from stains, spills and wear. Chemical Resistant Clear Epoxy CR130 has been developed specifically for Australian conditions using the latest epoxy technology. It provides excellent protection against weathering conditions and the splash and spillage of a wide range of chemicals.

Chemical Resistant Clear Epoxy CR130 provides a highly durable, chalk resistant, wear and chemical resistance surface for concrete floors. High quality topcoat epoxy floor coating system that is solvent free when used as a clear un-pigmented coating or binder. The product can be tinted in all Australian Standard Colours. This coating has specially developed to be incorporated with non-slip materials and a large number of decorative materials to provide a floor finishing system, with functionality and style. The surface may be laid as a thin film using roller applicator. The thickness of the coating can be reduced by addition of Diluent. Aggregates may be added to the blend to create a non-slip flooring finish. Guaranteed modern, hygienic, functional and economical surface.



MATERIALS



CHEMICALS



RESINS



EQUIPMENT

Ph: (08) 9364 7446 | info@shimi.com.au | ABN: 28 622 871 283 | www.shimi.com.au

Features

Chemical Resistant Clear Epoxy CR130 is supplied in two pack kit, Part A (Resin) and Part B (Curative or Hardener). Other parts such as pigment, flakes, decorative and non-slip materials can be supplied separately. Selected features of Chemical Resistant Clear Epoxy CR130:

- Modern, Hygiene, Functional and Economical.
- Heavy duty clear or pigmented coating for concrete and polished concrete floors.
- Highly resistant to chemical attack and pedestrian or vehicular traffic.
- Can be used in conjunction with graded aggregates to produce durable decorative floor finishes.
- Long lasting and easily maintained with good resistance to a wide range of domestic and commercial chemicals.
- Solvent free when used as a clear unpigmented coating or binder.
- Outstanding water resistance.
- Seamless, easy to clean and maintain.
- Suitable for Flake Flooring systems, see SHIMI FLAKE flooring system.
- Superior Chemical Resistant Finished surface
- Excellent UV stability
- Solvent Free (Unless you apply Diluent for thickness control)
- Engineered formulation for trafficable area with high mechanical strength
- DIY Friendly, easy to apply and curable over a wide range of temperature
- Available with a wide range of Flakes for decorative concrete
- Ideally compatible for Non-Slip Flooring System

Coverage

1L covers approximately 5sqm per coat, depend on the conditions of the surface.

First coat usually consumes more and the second coat less.

For Pour-On applications and metallic effects, 1L/sqm is recommended to achieve 1000micron ideal thickness.

Applications

Roller, Brush or Squeegee.

Dry Time at 25°C

Pot Life:	45 minutes at 25°C
Tack Free:	2-3 hours
Thin Film Set:	8 Hours (Min, depending on temperature and humidity)
Deep Cast Set:	24 Hours (Min, depending on temperature and humidity) 10mm Max
Dry Cured:	12-16 hours – Foot Traffic (depending on temperature and humidity)
Fully Cured:	7 days (Vehicle Traffic)
Re-Coat:	Over night