

RESIDENTIAL  
& COMMERCIAL

INDUSTRIAL  
& MARINE

ART  
& CRAFT

**SHIMICOAT**  
SURFACE SOLUTIONS



# Slip Resistant Clear Polyaspartic Floor Finishing System

*Grit sizes to Australian Standard R9-R13*

## *An Installation Guide*

SlipRes Xtra Grip Materials are fine white granules used to increase slip resistance on floors when used in conjunction with resinous and solvent based coating systems. SlipRes can be applied while applying Ultra Clear Polyaspartic TOPCOAT 1A:1B. SlipRes Clear Polyaspartic floor shall be applied in situations where you desire to maintain the look of your surface. This system can be applied with Clear Polyaspartic, Tinted Polyaspartic or even in combination with Flake floor or Metallic finish surface.

### Products and Materials

1. Polyaspartic Resin – Clear or Tinted
2. Xtra Grip SlipRes Materials or SlipRes Ceramic
3. Diluent / Thinner

### Tools:

1. Electric mixer or stick for missing resin
2. Brush and Rollers
3. Extendable Handle / Pole
4. Vacuum or blower to clean up the surface
5. Spike Shoes (if you need to walk over the wet resin surface)



 MATERIALS  CHEMICALS  RESINS  EQUIPMENT

Ph: (08) 9364 7446 | [info@shimi.com.au](mailto:info@shimi.com.au) | ABN: 28 622 871 283 | [www.shimi.com.au](http://www.shimi.com.au)

## Advantages:

- Ideal SlipRes floor while maintaining your current surface appearance.
- Generally, increases abrasion resistance of solvent based coatings.
- Does not detract from aesthetic appeal of most decorative surface.
- Similar to metal enforcement in concrete matrix, SlipRes Xtra Grip increases the durability of your surface coating materials known as Ultra Durability Plus (UDP)



## Installation:

### Surface Preparations:

1. Prepare the surface in accordance to SHIMICOAT surface preparation manual to ensure ideal bonding.
2. Ensure the surface is perfectly clean and free of oil and grease.
3. Vacuum and/or blow out to remove dust from the surface.
4. Tape all around the walls and cover all surfaces that you wish NOT to be Polyaspartic coated.

**NOTE:** For further information on surface preparation, please refer to our brochure, website or contact Shimicoat technical representative.

### Polyaspartic Coating:

1. Once the surface is prepared and you are set for coating application, commence mixing resins.
2. Mix Part A with Part B in accordance to label instruction. Ultra Clear Polyaspartic shall be used at 1A:1B (by weight or volume) blend ratio. Tinted Polyaspartic shall be used at 1.5A:1B (by volume) blend ratio.
3. Once mixed, you are on the clock, 15min to complete coating application.
4. Apply to the surface using a roller or brush, depending on the size of your surface. Use brush/mini-roller to coat over the edges and corners.
5. Using a Fertilizer Spreader or a similar tool to sprinkle Xtra Grip SlipRes granules over the entire surface.
6. You can use your roller to go over the surface again (without Polyaspartic) just gently over the entire surface to maintain uniformity of the finish surface.
7. Let it cure (4 hours) depending on temperature.
8. Feel free to apply another clear topcoat Polyaspartic over the surface.

**NOTE:** Add Polyaspartic Diluent, EpoDil or Xylene up to 5% to thin the product, only if required and only for the first coat. During winter, you may need more thinner/diluent to reduce product viscosity, for ease of application.

For further advise, please contact technical team at Shimicoat or refer to product brochure or our website.

End of Procedure.

